

TECHNICAL DATA SHEET

SM1500 24K C12MM/ C24MM

ARTICLE CODE SM 1500 24K C12MM/ C24MM

PATTERN Chopped Carbon Fiber

FINISH Carbon Forged

COMPOSITION 58% Carbon fiber, 42% Epoxy Resin

MATERIAL DESCRIPTION

Carbon fiber SMC is a is a sheet-type intermediate material made of high strength chopped carbon fiber impregnated with thermoset resin.

The random distribution of the chopped fiber is a feature of the material itself, providing discontinuity and an unrepeatable visual aspect.

	VALUE	STANDARD
Nominal weight (g/sqm)	870 ± 5%	ISO 3374
Standard width (mm) ¹	1200 ± 1.5%	UNI EN 1773
Cured ply thickness (mm)	1.01*	-

¹Measured between selvedges

^{*}Indicative data calculated for RC 42%.

FIBER PROPERTIES		
	Random	
Material variants	24K Chopped Carbon HS	
Filament Yield (Tex)	1600	
Fiber density ^{2, 3}	1.80	

²Depending on order and yarn specification

Note: All technical information contained in this document are given in good faith and are based on tests believed to be reliable, but their accuracy and completeness are not guaranteed. They do not constitute an offer to any person and shall not be deemed to form the basis of any contract. Accordingly, the user shall determine the suitability of the products for their intended use prior to purchase and shall assume all risk and liability in connection therewith. The information contained herein is under constant review and liable to be modified. All products are sold subject to Microtex Composites Srl terms and conditions of sale. Copyright 2020 - Microtex Composites Srl. All rights reserved worldwide. All trademarks or registered trademarks are the property of their respective owners.

Microtex Composites S.r.l.

Via del Pozzo di San Sebastiano, 15/C 51100 Pistoia (Italy)
Tel. +39 0574 627298
info@microtexcomposites.com





³No measure, certified by supplier



TECHNICAL DATA SHEET

SM1500 24K C12MM/ C24MM

ADDITIONAL INFORMATION

Available Chopped Fibre length:

- 12 mm
- 24 mm

Note: All technical information contained in this document are given in good faith and are based on tests believed to be reliable, but their accuracy and completeness are not guaranteed. They do not constitute an offer to any person and shall not be deemed to form the basis of any contract. Accordingly, the user shall determine the suitability of the products for their intended use prior to purchase and shall assume all risk and liability in connection therewith. The information contained herein is under constant review and liable to be modified. All products are sold subject to Microtex Composites Srl terms and conditions of sale. Copyright 2020 - Microtex Composites Srl. All rights reserved worldwide. All trademarks or registered trademarks are the property of their respective owners.



