

ARTICLE CODE	GG 1250 DO 24K
PATTERN	Double weave
FINISH	Loomstate
COMPOSITION	100% Carbon fiber

TECHNICAL DATA	VALUE	STANDARD
Nominal weight (g/sqm)	1250 ± 5%	ISO 3374
Standard width (mm) ¹	1000 /1250 ± 1.5%	UNI EN 1773
Fabrck thickness (mm)	2,50 ^{2*}	UNI EN ISO 5084

¹Measured between selvages

*indicative data

CONSTRUCTION		
	Warp	Weft
Material	24K Carbon fiber HS	24K Carbon fiber HS
Setting (thr/cm)	3,7 ± 4% [ISO 4602 (TA)]	3,7 ± 4% [ISO 4602 (TA)]
Weight ditribution (%)	50	50

FIBER PROPERTIES		
	Warp	Weft
Nominal Yield ²	1600 Tex	1600 Tex
Fiber density ²³	n.g.	n.g.
Twist ²	n.g.	n.g.

²Depending on order and yarn specification

³No measure, certified by supplier

ADDITIONAL INFORMATION

Hight drapability

NOTE: All technical information contained in this document are given in good faith and are based on tests believed to be reliable, but their accuracy and completeness are not guaranteed. They do not constitute an offer to any person and shall not be deemed to form the basis of any contract. Accordingly, the user shall determine the suitability of the products for their intended use prior to purchase and shall assume all risk and liability in connection therewith. The information contained herein is under constant review and liable to be modified. All products are sold subject to Microtex Composites Srl terms and conditions of sale. Copyright 2020 - Microtex Composites Srl. All rights reserved worldwide. All trademarks or registered trademarks are the property of their respective owners.

Doc no. TDS-F_1
Rev 00
Issued 16/11/18
Author L. Gucci